



Description:

0.5mm²; BS6004, H05V2-U; 60227 IEC 07.

Conductor:

0.5mm² (1/0.8mm) plain annealed copper wire meeting the requirements of BS 6360, class 1, and IEC 60228, class 1.

Insulation:

PVC compound meeting the requirements of BS 7655: section 3.1, type T13 and IEC 60227, type PVC/E.

Minimum average wall thickness = 0.6mm.

Minimum average diameter = 1.9mm.

Maximum average diameter = 2.3mm.

Part Number Table

Description	Part Number
Wire, HR, White, 1/0.8mm, 100M	1/0.8 HR White 100M
Wire, HR, White, 1/0.8mm, 500M	1/0.8 HR White 500M
Wire, HR, Blue, 1/0.8mm, 100M	1/0.8 HR Blue 100M
Wire, HR, Blue, 1/0.8mm, 500M	1/0.8 HR Blue 500M
Wire, HR, Brown, 1/0.8MM, 100M	1/0.8 HR Brown 100M
Wire, HR, Yellow/Green, 1/0.8mm, 100M	1/0.8 HR Yellow/Green 100M
Wire, HR, Red, 1/0.8mm, 100M	1/0.80Red100
Wire, HR, Black, 1/0.8mm, 100M	1/0.80Black100
Wire, HR, Black, 1/0.8mm, 500M	1/0.80Black500

Disclaimer This data sheet and its contents (the "Information") belong to the Premier Farnell Group (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Pro-Power is the registered trademark of the Group. © Premier Farnell plc 2009.