

<b>Vermason</b>		Product Information		No: PIS 129	
	Page 1 of 1	Issue No 2	Date 29 April 1999	Approved by:	

**ELECTROSTATIC SHIELDING BAGS**  
Code BB4...

PROPERTIES	UNIT	TYPICAL VALUES	TEST METHODS
<b>Surface Resistivity:</b>			
Inner Layer	$\Omega/\text{sq}$	$<10^{12}$	EOS/ESD S11.11.1993
Metal Layer	$\Omega/\text{sq}$	$<10^2$	EOS/ESD S11.11.1993
Outer Layer	$\Omega/\text{sq}$	$<10^{12}$	EOS/ESD S11.11.1993
EMI Shielding	dB@1-10GHz		MIL SPEC B-81705C
Charge Decay	sec	<0.1	EIA 541
Shielding (Capacitance Probe)		5V differential <20 Milliseconds	EIA 541
Charge Generation	NC/in <sup>2</sup>	Teflon: -0.03 Quartz: +0.10	Modified Inclined Plane
<b>Thickness:</b>			
Polyester	mil	0.5	ASTM D2103
Antistatic polyethylene	mil	2.3	ASTM D2103
Tensile strength	lbs/in <sup>2</sup>	>15	ASTMD882
Puncture resistance	lbs	>10	FTMS 10001C
Transparency	%	>40	ASTM D-1003-77
MVTR	g/100in <sup>2</sup> /24h	<0.2g @ 1001F	ASTM F 1249
Abrasion Resistance	cycles	>100	Sutherland (.0000 Steel Wool)

Other properties: Free from amine/amides/heavy metals. Polycarbonate compatible.