ALL RIGHTS RESERVED. NO PORTION OF THIS PUBLICATION, WHETHER IN WHOLE OR IN PART CAN BE REPRODUCED WITHOUT THE EXPRESS WRITTEN CONSENT OF SPC TECHNOLOGY.

		REVISIONS	DDC, NO, SPC-FD04 * Effective: 12/21/98 * DCP No: 680						
DCP #	REV	DESCRIPTION	DRAWN	DATE	CHECKD	DATE	APPRVD	DATE	
1955	Α	RELEASED	NL	07/08/09	NL	07/10/08	JN	07/10/08	

SPC Type	Standard Wire Gauge (AWG)	Diameter		Alloy Content Tin/	Weight	Flux %	Flux Type	Softening Point Celsius	Acid Number (mgKOH/ G	SIR (Surface Insulation	
NO.		Inches	mm	Lead				(Flux Extract)	Sample)	Resistance)	
SPC22123	23	0.025	0.63	60/40							
SPC22124	21	0.032	0.81	60/40		3.30%				>1.0 x 10 ⁹	
SPC22126	21	0.032	0.81	60/40							
SPC22127	19	0.04	1.01	60/40							
SPC22128	18	0.05	1.27	60/40			Rosin (RA)	80°C			
SPC22129	16	0.062	1.57	60/40	1lbs.				150-160		
SPC22130	25	0.02	0.5	60/37							
SPC22131	23	0.025	0.63	60/37							
SPC22132	21	0.032	0.81	60/37							
SPC22133	19	0.04	1.01	60/37							
SPC22134	18	0.05	1.27	60/37							
SPC22135	16	0.062	1.57	60/37							
SPC22125	23	0.025	0.63	60/37	0.5 lbs.						
SPC22136	21	0.032	0.81	60/40	1lbs.		Mater Calubia	C09C	400 400		
SPC22137	21	0.032	0.81	60/37	1lbs.		Water Soluble	60°C	120-130		
SPC22138	21	0.032	0.81	60/37	1lbs.		Rosin (RMA)	92°C	150-160		
SPC22139	21	0.032	0.81	60/37	1lbs.	2.20%	No Clean	75°C	190-210		
SPC22140	25	0.02	0.5	60/37	1lbs.	2.20%	ino clean	75°C	190-210		

Notes:

- The Water Soluble Solder has a flux within that must be cleaned; therefore, the Flux Extract Softening Point Test does not apply.
- 2. Acid Number test is based upon the IPC-TM-650 test method.
- 3. Flux Appearance: Amber Solid

Rosin Activated (RA) Flux:

It is a high activity core flux designed for excellent instant wetting action, even on Nickel surfaces. Although it is a RA-based material, the residues are non-corrosive if not cleaned. Per J-STD-004. Classified as ROM1 flux.

Water Soluble Flux:


It is a high-activity water-soluble core flux for soldering difficult metals. It is designed for optimal cleanability, along with minimal smoke and odor. Its residues must be removed. It is classified as ORH1 per J-STD-004.

Rosin Mildly Activated (RMA) Flux:

It is an RMA based core flux that provides wetting action comparable to typical RA flux. Although it is an RMA-based material, the residues are non-corrosive if not cleaned. It is categorized as ROL1 per J-STD-004.

No-Clean Flux:

It is a halide-free, rosin based no-clean core flux that provides excellent wetting combined with optimal reliability and cosmetics. It is compliant to Bellcore GR-78 and is classified as ROL0 per J-STD-004.



SPC-F004.DWG

DISTALAMENT AND TECHNICAL INFORMATION CONTAINED HEREIN ARE BASED UPON INFORMATION AND/OR TESTS WE BELIEVE TO BE ACCURATE AND RELIABLE. SINCE CONDITIONS OF USE ARE SECTION DUTE CONTROL. THE USER'S RIALL DETERMINE THE SUBMENUT OF THE PRODUCT FOR THE INTENDED USE AND ASSUME ALL RIBK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.				SPC TECHNOLOGY							
UNLESS OTHERWISE	DRAWN BY:	DATE:	DRAWING TITLE:								
SPECIFIED,	Jason Nash	07/08/09			SOLDER WIRE						
DIMENSIONS ARE	CHECKED BY:	DATE:	SIZE	DWG. NO.			ELEC	TRONIC FILE	REV		
FOR REFERENCE PURPOSES ONLY,	Jason Nash	07/10/08	A		TA-885		TA-885.DWG A				
	APPROVED BY:	DATE:			U.O.M.: INCHES [mm]						
	Jason Nash	07/10/08	SCALE	E: NTS				SHEET: 1 C			