


Product Number: 0305-0-15-15-47-27-10-0



Basic Part Number	Length L	Dia. D
0305-0	.095	.056
0305-1	.105	.058
0305-2	.155	.058

DATA SHEET

Description:

0305 - Receptacle With No Tail Accepts .025-.037 .025 sq post diameter leads.

Packaging:

Packaged in Bulk

0305-X-15-XX-47-XX-10-0

Solder mount in .059/.061 mounting hole

Mill-Max Part Number	Shell Plating	Contact Plating	RoHS Compliant
0305-0-15-15-47-27-10-0	10 $\mu^{\prime\prime}$ Gold over Nickel	30 µ" Gold over Nickel	RoHS 2002/MS/EC
CONTACT:			
Contact Used: #47, Standard 6 Finger Con Current Rating = 4.5 Amps	ntact 1000	#47 CONTACT	
BERYLLIUM COPPER ALLOY 172 (UNS) ASTM B 194		IAL INSERTION FORCE	
Properties of BERYLLIUM COPPER:	s — EXT	RACTION FORCE	
Chemical composition: Cu 98.1%, BeTemper as stamped: TD01	1.9%		
Properties after heat treatment (TH01):			
 Hardness: 36-43 Rockwell C Mechanical Life: 100 Cycles Min. Density: .298 lbs/in3 Electrical Conductivity. 220/ LACS* 	10 00 10 00		33 35 4
 Electrical Conductivity: 22% IACS* Resistance: 10 miliohms Max Operating Temperature: -55°C/+125° Melting point: 980°C/865°C (liquidus/ 		0.02 0.02 0.02 0.02 0.02 0.02 0.02 0.02	0.035 0.035 0.036 0.037 0.037

*International Annealed Copper Standard, i.e. as a % of pure copper.

[†]Since BeCu loses its spring properties over time at high temperatures; it is rated for continuous use up to 150°C. For applications up to 300°C, Mill-Max offers many contacts in Beryllium Nickel. Contact Tech Support for more info.

SHELL MATERIAL: BRASS ALLOY (UNS C36000) per ASTM B 16

Properties of BRASS ALLOY:

- Chemical composition: Cu 61.5%, Zn 35.4%, Pb 3.1%⁺
- Hardness as machined: 80-90 Rockwell B
- Density: .307 lbs/in3
- Electrical conductivity: 26% IACS*
- Melting point: 900°C/885°C (liquidus/solidus)

+(3 to 4% lead is used to permit "free machining" and is permitted by EC Directive 2002/95Annex 6; so all pin materials are RoHS compliant)

*International Annealed Copper Standard, i.e. as a % of pure copper.