

[Products](#)

[Technical](#)

[About Us](#)

[Contact Us](#)

Catalog Part Search:




Figure 2

Part Number: 0444173551
 Frequency Range: Broadband Frequencies 25-300 MHz (43 & 44 materials)
 Description: CSRA29/29/42-44-19 44 ROUND CABLE CORE ASSEMBLY
 Application: Suppression Components
 Where Used: Cable Component
 Part Type: Round Cable Snap-its
 Preferred Part:

Part Type Information

Mechanical Specifications

Weight: 78.00 (g)

[View Chart Legend](#)

Dim	mm	mm tol	nominal inch	inch misc.	Land Patterns					Winding Information				
					V	W (ref)	X	Y	Z	Turns Tested	Wire Size	1st Wire Length	2nd Wire Length	
A	29.20	-	1.150	-	-	-	-	-	-	-	-	-	-	-
B	18.80	-	0.740	-	Reel Information					Pkg Size				
C	42.00	-	1.650	-	Tape Width mm	Pitch mm	Parts 7" Reel	Parts 13" Reel	Parts 14" Reel	Connector Plate				
D	14.70	-	0.579	-	-	-	-	-	-	# Holes	# Rows			
E	-	-	-	-	Cable Information									
F	-	-	-	-	Max Diameter	Max Dimension	Solid Equivalent	Flat Cable Cores						
G	-	-	-	-	18.500	-	-	-						
H	-	-	-	-	.728	-	-	-						
J	-	-	-	-	-	-	-	-						
K	-	-	-	-	-	-	-	-						

Electrical Specifications

Typical Impedance (Ω)	
10 MHz	50
25 MHz ⁺	95
100 MHz ⁺	195
250 MHz	322

Electrical Properties	
-	-

Ferrite Material Constants

Specific Heat	0.25 cal/g ^o C
Thermal Conductivity	10x10 ⁻³ cal/sec/cm ^o C
Coefficient of Linear Expansion	8 - 10x10 ⁻⁶ / ^o C
Tensile Strength	4.9 kgf/mm ²
Compressive Strength	42 kgf/mm ²
Young's Modulus	15x10 ³ kgf/mm ²
Hardness (Knoop)	650
Specific Gravity	≈ 4.7 g/cm ³

The above quoted properties are typical for Fair-Rite MnZn and NiZn ferrites.


44 Material Specifications:

A NiZn ferrite developed to combine a high suppression performance, from 30 MHz to 500 MHz, with a very high dc resistivity.


SM beads, PC beads, wound beads, round cable snap-its, and connector EMI suppression plates are all available in 44 material.

Property	Unit	Symbol	Value
Initial Permeability @ B < 10 gauss		μ _i	500
Flux Density	gauss	B	3000
Field Strength	oersted	H	10
Residual Flux Density	gauss	B _r	1100
Coercive Force	oersted	H _c	0.45


Loss Factor @ Frequency	10^{-3} MHz	$\tan \delta/\mu_i$	125
Temperature Coefficient of Initial Permeability (20-70°C)	%/°C		0.75
Curie Temperature	°C	T_c	>160
Resistivity	Ω cm	ρ	1×10^9




Measured on a 17/10/6mm toroid using the HP 4284A and the HP 4291A.



Measured on a 2644000301 using the HP4291A.




Measured on a 17/10/6mm toroid at 100kHz.



Measured on a 17/10/6mm toroid at 10kHz.

Impedance Curve

0444173551



Impedance, reactance, and resistance vs. frequency.

(c) Copyright www.fair-rite.com 2007. All Rights Reserved. Site Map
Telephone: (888)324-7748 Application Engineering questions: ferrites@fair-rite.com Web Site Questions: webmaster@fair-rite.com