



- Conductive elastomers • Knitted wire mesh
- Conductive coatings, sealants, adhesives
- Cable shielding products • EMI/ESD shielding laminates
- Shielded vents and windows
- FCC/VDE and TEMPEST testing

LEADER IN EMI SHIELDING INNOVATION, DESIGN, AND TEST TECHNOLOGY


## CHO-FAB™ and CHO-FOIL® Family of EMI Shielding Tapes with Conductive Adhesive

CHO-FAB™ tape is a corrosion resistant nickel-plated cloth coated with Chomerics' highly conductive pressure-sensitive adhesive. This adhesive contains a uniform dispersion of conductive particles that create a very low electrical resistance through the tape. This feature results in superior shielding performance in a wide variety of environmental conditions.

CHO-FAB tape is extremely strong, lightweight and has excellent conformability/wrapability to enhance shielding performance and appearance. Use of corrosion resistant nickel-plated cloth and Chomerics' superior metal-particle-filled conductive adhesive technology produces a tape used in a wide variety of EMI shielding and grounding applications.

CHO-FOIL® tapes are an economical EMI shielding solution for a variety of commercial uses. The tapes are available in copper, aluminum, or tinned copper foil backed with Chomerics' highly conductive pressure-sensitive adhesive. The copper version of CHO-FOIL tape meets the requirements of MIL-T-47012 and the tinned copper foil tape meets MIL-T-10727 for corrosion resistance.

CHO-FOIL and CHO-FAB shielding tapes are available in standard 36 yard length rolls, and die cut custom configurations.\* For applications requiring surface conductivity only, copper tape is available with a non-conductive adhesive.



### TYPICAL APPLICATIONS

- Provides a low impedance connection between a braided cable shield and the metal connector backshell in molded cables. An effective EMI shielded assembly can be achieved without soldering the tape to the braid or backshell.
- EMI radiation measurement troubleshooting, using CHO-FOIL tape to shield ventilation slots or seam gaps.
- Provides electrical continuity in seams of EMI shielded rooms and electronic enclosures.
- Supplies electrical contact to surfaces that can't be soldered to, such as conductive plastic or aluminum.
- EMI shield for cables by wrapping the tape around the cable. An overlap is recommended.
- ESD shielding.
- Provides corrosion-resistant ground contact points.
- Fabric tape available where weight and flexibility are important such as for wrapping cables.

\*A non-conductive version of CHO-FOIL copper tape is available for a more attractive surface appearance.

**APPLICATION NOTES**

1. To ensure maximum adhesion, remove all surface oils and dust from the areas to be taped.
2. When applying the tape, note that oils from the hand can affect adhesion.
3. These tapes are compatible with industry standard tape dispensers.

Technical Data

PROPERTY	TEST METHOD	TYPICAL VALUES						
Part Number Prefix	—	CCH	CCE	CCJ	CCK	CCD	CAD	CFT
Fabric/Foil Type	—	1 oz. RA Copper	1 oz. embossed RA Copper	Aluminum	1 oz. Tin-Plated Copper	1 oz. RA Copper	Aluminum	Nickel Plated Cloth
Fabric/Foil Thickness, mils (mm)	—	1.4 (.036)	1.4 (.036)	2 (.051)	1.6 (.041)	1.4 (.036)	2 (.051)	5 (.127)
Adhesive Type	—	Particle Filled Acrylic Pressure Sensitive						
Adhesive Thickness, mils (mm)	—	1.5 (.038)				2 sides: 1.5 each (.038 each)		1.5 (.038)
Total Thickness, mils (mm)	—	2.9 (.074)	4 (.110)	3.5 (.089)	3.1 (.079)	4.4 (.112)	5 (.127)	6.5 (1.651)
Temperature Range, °F (°C)	—	-40 to 400 (-40 to 205)						-40 to 180 (-40 to 82)
Electrical Resistance, ohms/in <sup>2</sup> (ohms/cm <sup>2</sup> )	MIL-STD-202C	<.003 (.0004)	<.003 (.0004)	<.010 (.002)	<.003 (.0004)	<.010 (.002)	<.010 (.002)	<.100 (.020)
Flame Resistance	UL Subject 510	PASS	MEETS	PASS	PASS	MEETS	MEETS	N/A
Adhesion to Aluminum oz./inch [ppj] (N/m)	ASTMD1000	>40 [2.5] (438)						

**ORDERING INFORMATION**

Standard rolls can be ordered through Chomerics' authorized distributors using these part numbers:

CCH - 36 - 101 - <u>ZZZZ</u>	Copper foil, conductive adhesive
CCE - 36 - 101 - <u>ZZZZ</u>	Copper foil, conductive adhesive, embossed
CCH - 36 - 301 - <u>ZZZZ</u>	Copper foil, non-conductive adhesive
CCJ - 36 - 201 - <u>ZZZZ</u>	Aluminum foil, conductive adhesive
CCK - 36 - 101 - <u>ZZZZ</u>	Tin plated copper foil, conductive adhesive
CCD - 36 - 101 - <u>ZZZZ</u>	Copper foil, conductive adhesive 2 sides
CAD - 36 - 101 - <u>ZZZZ</u>	Aluminum foil, conductive adhesive 2 sides
CFT - 36 - 101 - <u>ZZZZ</u>	Nickel-plated fabric, conductive adhesive

ZZZZ = WIDTH

<u>050</u>	<u>100</u>	<u>150</u>	<u>200</u>	<u>300</u>	<u>400</u>	<u>600</u>	<u>800</u>	<u>1200</u>	<u>2400</u>
0.5 in.	1.0 in.	1.5 in.	2.0 in.	3.0 in.	4.0 in.	6.0 in.	8.0 in.	12 in.	24 in.
12.7mm	25.4mm	38.1mm	50.8mm	76.2mm	102mm	152mm	203mm	305mm	610mm

(Other widths available up to 24 in. [61 cm])

Please consult Chomerics' Applications Engineering Department for assistance with a custom application involving a need for material in other than slit roll form.

NOTE: The following table represents actual experimental test data taken according to Chomerics internal test procedures. This data differs from the previous table due to differences in test methods.

Table A: Reliability Data

TEST	TEST METHOD	CCH	CCE	CCJ	CCK	CCD	CAD	CFT
Initial Surface Resistivity (SR) (milliohms)*	CHO-TP-57***	<2	<2	<2	<2	N/A	N/A	<100
Initial Through Resistivity (TR) (milliohms)*	CHO-TP-57***	<3	<3	<35	<2	<15****	<100****	<100
Initial Peel Strength OZ./inch [ppi] (N/m)**	ASTMD1000	44.8 [2.8](490)	44.8 [2.8](490)	51.2 [3.2](560)	46.4 [2.9](508)	48 [3.0](525)	70.4 [4.4](710)	44.8 [2.8](490)
Initial Taber Abrasion Surface Resistivity (SR) (milliohms)	CHO-TP-57***	<6	<3	<6	<9	N/A	N/A	<100
Heat Aging 185°F (85°C)/ 168 hrs.	SR (milliohms)*	<10	<2	<20	<2	N/A	N/A	<100
	TR (milliohms)*	<16	<3	<22	<2	<7****	<60****	<150
	Peel, OZ./inch [ppi] (N/m)**	ASTMD1000	57.6 [3.6](630)	62.4 [3.9](683)	76.8 [8.0](840)	67.2 [4.2](735)	73.6 [4.6](805)	78.4 [4.8](840)
Heat Aging 250°F (121°C)/ 168 hrs.	SR (milliohms)*	<10	<3	<20	<2	N/A	N/A	<100
	TR (milliohms)*	<70	<3	<23	<2	<3****	<10****	<150
	Peel, OZ./inch [ppi] (N/m)**	ASTMD1000	57.6 [3.6](630)	59.2 [3.7](648)	75.2 [4.7](823)	51.2 [3.2](560)	70.4 [4.4](770)	84.8 [5.3](928)
Heat Aging with Humidity 95% RH/ 185°F (85°C)/	SR (milliohms)*	N/A	N/A	N/A	<2	N/A	N/A	<100
	TR (milliohms)*	N/A	N/A	N/A	<2	<115****	<150****	<150
	Peel, OZ./inch [ppi] (N/m)**	ASTMD1000	N/A	N/A	N/A	78.4 [4.9](858)	78.4 [4.9](858)	84.8 [5.3](928)
Salt fog corrosion/ 168 hrs.	SR (milliohms)*	N/A	N/A	N/A	<2	N/A	N/A	<100
	TR (milliohms)*	N/A	N/A	N/A	<2	<275****	<600****	<1000
	Peel, OZ./inch [ppi] (N/m)**	ASTMD1000	N/A	N/A	N/A	76.8 [4.8](840)	62.4 [3.9](683)	80 [5.0](875)
Taber abrasion 500 gramweight, CS-10 wheel, 500 cycles	CHO-TP-57***	<3	<5	<2	<6	N/A	N/A	<175

N/A = Not Applicable

\* All measurements of surface resistivity and through resistivity made at ambient temperature with tapes mounted on tinned copper substrate except for taber abrasion where a plastic substrate was used.

\*\* 90° peel strength tests were done on an Instron at 2 inches per minute with tapes on a 2024 aluminum substrate.

\*\*\* CHO-TP-57 available from Chomerics on request.

\*\*\*\* Through resistivity measurement of double sided adhesive tapes done with tapes flanged between 2024 aluminum substrates.



Chomerics  
Div. of Parker Hannifin Corp.  
77 Dragon Court  
Woburn, MA 01888-4014  
Tel: 781-935-4850  
FAX: 781-933-4318

[www.chomerics.com](http://www.chomerics.com)

Parker Hannifin PLC  
Chomerics Division  
Parkway, Globe Park  
Marlow, Bucks., SL7 1YB, England  
Tel: (44) 1628 486030 FAX: (44) 1628 890053  
France Freephone Tel: (0590) 8170  
Germany Freephone Tel: (0130) 818074

NOTICE: The information contained herein is to the best of our knowledge true and accurate. However, since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own tests to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated on Chomerics' invoice, quotation, or order acknowledgement. We disclaim any and all liability incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use. The items described in this document are hereby offered for sale by Parker Hannifin Corporation, its subsidiaries or its authorized distributors. This offer and its acceptance are governed by the provisions in the document entitled "Offer of Sale," available from Chomerics on request.