
## **Soldering Tips**





## Coating Standard for Soldering Tips:

Alloy Iron coating thickness :  $0.3 \mu m$  Nickel coating thickness :  $0.2 \mu m$  Chrome coating thickness :  $0.2 \mu m$ 

Alloy Iron coated iron tips perform excellent on temperature during  $360^{\circ}\text{C}$  and  $380^{\circ}\text{C}$ 

It can only work 4-5 hours if tips continuous get heat up beyond 450°C Chrome layer will lose effect if temperature is up to 500°C

Dimension tolerance is +0.02 mm

## **Part Number Table**

Description	Part Number
Tip, Chisel, 0.8 mm, PK10	21-10140
Tip, Chisel, 1.2 mm, PK10	21-10142
Tip, Chisel, 1.6 mm, PK10	21-10144
Tip, Chisel, 2.4 mm, PK10	21-10146
Tip, Conical, 0.5 mm, PK10	21-10148
Tip, Conical, 0.2 mm, PK10	21-10150
Tip, Chisel, Angled, 2 mm, PK10	21-10152
Tip, Chisel, Angled, 3 mm, PK10	21-10154
Tip, Chisel, Angled, 4 mm, PK10	21-10156
Tip, Conical, Micro, 0.2 mm, PK10	21-10158

Dimensions: Millimetres (Inches)

Important Notice: This data sheet and its contents (the "Information") belong to the members of the Premier Famell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. TENMA" is the registered trademark of the Group. © Premier Farnell plc 2011.

